



# PIX - ULTRA FAST CURE EVA ENCAPSULANT FILM : BOTTOM LAYER - PIX UFC-B



Solar EVA Encapsulant Sheet

## ABOUT US

PIXON houses clean room and environment controlled facility up to 1 GW manufacturing line for EVA Encapsulant films.

PIXON Ultra Fast Cure EVA Encapsulant Films are specifically designed for enhancing the durability and increasing the performance of solar modules and are suitable for all types of Crystalline and Thin film PV modules with shorter cycling time that speeds up your module production with Excellent Transparency, High Reflectivity ( Back side Film ) increased Production Yield, Snail Trail Resistant, PID-Resistant, Lower Shrinkage, Excellent Performance with UV and Weather Stability.

PIXON EVA Encapsulant Film is proven for single stage as well as short cycle Multi Stage Lamination Processes.

## CERTIFICATIONS



TUV tested - DH, EVA Encapsulant Thermal & Electrical Properties  
TUV CTI Report : IEC 60112:2020



UL Certified  
Certificate Number E526148

\*Due to continuous product updation, specifications may change without notice.

### PIXON GREEN ENERGY PRIVATE LIMITED

**Manufacturing Unit:** R.S. No.: 157/1, 158/1, 158/2, 165/1, 166 of Khijadiya Nana, R.S. No.: 15/1, Rajkot - Jamnagar Highway, Paddhari, Rajkot - 360110

1800 108 8800 | sales@pixonenergy.com



**Solar is  
the new Green!**

# TECHNICAL DATASHEET



## PIX ULTRA FAST CURE BOTTOM EVA ENCAPSULANT FILM

### Technical Parameters For PIX UFC-B

	Particulars	Test Method	Unit	Values
Physical	Thickness	ASTM D 6988	µm	0.60 - 0.75 (± 5)
	Width	Scale	mm	Up to 1335 (As per Customer Requirement)
	Melting Point	ISO 11357	°C	70 ± 3
	Surface type	Visual	Unit	Both side Embossed
Thermal	Melt Index	ASTM D 1238	g/10min	25± 3
	Thermal Shrinkage	1600C/5 min On Glass Plate	%	≤ 2 % MD, ≤ 1.5 TD
	Water Absorption Test	ISO 62:200805	%	< 0.1
Electrical	Dielectric Strength	ASTM D 149 - 20	kv/mm	> 25
	Volume Resistivity	ASTM D 257	Ohm.cm	≥ 1x10
Optical	UV Cut Off	ASTM E 424	nm	360 ± 30
	Transmittance	ASTM D 424	%	≥ 91 <sup>16</sup>
	Refractive Index	ISO 489	-	1.48
Mechanical	Peel Strength (EVA Encapsulant - Glass)	ASTM D 903	N/cm	≥ 70
	Peel Strength (EVA Encapsulant - Backsheet)	ASTM D 903	N/cm	≥ 70
	Tensile Strength	ASTM D 638	MPa	12 ± 3
	Elongation	ASTM D 638	%	≥ 500
	Shore hardness	ASTM D 2240	SHORE-A	70 ± 5
Chemical	Gel Content	ASTM D 2765 / Oven Method	%	≥ 75

Lamination Properties	Lamination Parameter	Single Stage	Double Stage(Stage 1)	Double Stage(Stage 2)
	Vacuum Time	3 - 5 min	3 - 4 min	-
	Lamination Time	7 min	2 - 4 min	6 - 7 min
	Temperature	148 - 152°C	148 - 152°C	-

\*Laminator recipe depends on type of laminator.

- Temperature and Vacuum to be uniformly maintained across the laminator.
- Vacuum to be applied at -760 mm Hg. Periodic calibration of the machine input parameters to be done by Machine User.
- Lamination Parameters (cycle time) would vary from Laminator to Laminator also due to change in EVA Encapsulant/Module Width and Thickness of EVA Encapsulant, hence Extensive trials are suggested to get the desired results.

PACKAGING INFORMATION			
Unless specified, below is the standard packing data (for 500 micron thickness, 1123 mm width)			
Length/Roll	150 Meters	250 meters	300 meters
Nos of Rolls/Pallet	12	4	4
Total Linear Meters / Pallet	1800	1000	1200
Total SQM / Pallet	2021.4	1123	1347.6

Each Roll is sealed in a protective bag in corrugated box | Boxes are strapped on suitable pallets with Protection Angle Board.

**Storage Condition and Shelf Life:** Store in undamaged original packaging, temperature between 20°C and 30°C and humidity between 50-60% RH. Recommended use within 9 months from date of manufacture.

- The above technical information represents the typical range of properties and is believed to be correct as on date.
- This data should however not be used to establish specification limits or used as basis for design.
- PIXON gives no warranty and assumes no liability in connection with any use of this information and is subject to the PIXON general terms and conditions.
- Lamination parameters and Quality of other components of the laminate during module manufacturing impact on the overall performance of the module, and hence we recommend the user to carry out intensive trials to test suitability of this product and module laminating conditions.

